

# SPAR 75

## APPLICATIONS

Ceramics

## SPECIFICATIONS

### CHEMICAL ANALYSIS (%)

Parameter	Values (%)	Method
SiO <sub>2</sub>	66.5 ± 1.0	XRF
Al <sub>2</sub> O <sub>3</sub>	18.2 ± 1.0	XRF
Fe <sub>2</sub> O <sub>3</sub>	0.10 max	XRF
K <sub>2</sub> O	11.0 min	XRF
Na <sub>2</sub> O	2.50 ± 0.75	XRF
CaO	0.30 max	XRF
MgO	0.10 max	XRF
LOI	0.30 Typical	

### PARTICLE SIZE DISTRIBUTION (%)

Parameter	200 #
Residue on 200 #	Max 2.00

### PACKAGING

Product Form	Powder
Bag (kg)	25,40 & 50
Big Bag (kg)	800,1000,1200,1250,1350

These values do not represent a specification. The data quoted are determined by the use of Imerys Standard Test Methods, copies of which will be supplied on request. Every precaution is taken in production to ensure the products conform to our published data. Since the products are based on naturally occurring materials, we reserve the right to change these data should it become necessary. Sales are in accordance with our "Conditions of Sale", copies of which will be supplied on request.

Jan 2020

© Imerys Ceramics 2020

First Edition, Rev:00

### Contact

Imerys Ceramics (India) Pvt Ltd  
1-11-246 / 4F & 1-11-247/D  
4<sup>th</sup> floor, Surya Arcade  
Begumpet  
Hyderabad – 500 016  
India

Tel. +91 40 3058 6666

Fax: +91 40 3068 2266

### Email

info@imerys-ceramics.com

### Website

[www.imerys-ceramics.com](http://www.imerys-ceramics.com)